



Grigio Antico | Granite

Test	Std.	Unit	Ave. Value	Condition
Dry Density	EN 1936	(gr/cm3)	2.60	-
Saturated Density	EN 1936	(gr/cm3)	2.62	-
Porosity	EN 1936	(%)	1.28	-
Specific Gravity	EN 1936	(Kg/m3)	2.64	-
Water Absorption Under Atmosphere Pressure	EN 13755	(%)	0.49	-
Capillary Water Absorption	EN 1925	(Kg/m2)	0.54	-
Compressive Strength	EN 1926	(MPa)	86.16	Dry
Tensile Strength	ISRM 1981	(MPa)	8.54	Dry
Flexural Strength	EN 12372	(MPa)	12.51	Dry
Resistance to Salt Crystallization	EN 12370	(Mass loss %)	-0.26	After 48 Cycles
Resistance to Freeze-Thaw	EN 12371	(Mass loss %)	-0.04	After 48 Cycles
Resistance to Acid (H2SO4)	EN 13919	(Mass loss %)	-0.07	After 48 Cycles
Thermal Shock	EN 14066	(Mass loss %)	-0.021	After 48 Cycles

Details

- Formats Available | Slabs
- Thickness Available | 1cm, 2cm, 3cm
- Available Designs | Magma, Natural Lane Light, Hard Lane, Slope, Bedrock, Cliff, Satin
- Applications | Interior and Exterior Wall Cladding

Designs

