



Black Mood | *Granite*

Test	Std.	Unit	Ave. Value	Condition
Dry Density	EN 1936	(gr/cm3)	2.76	-
Saturated Density	EN 1936	(gr/cm3)	2.77	-
Porosity	EN 1936	(%)	0.31	-
Specific Gravity	EN 1936	(Kg/m3)	2.77	-
Water Absorption Under Atmosphere Pressure	EN 13755	(%)	0.11	-
Thermal Expansion Coefficient	EN 14581	10 ⁻⁶ C ⁻¹	6.8	-
Capillary Water Absorption	EN 1925	(Kg/m2)	0.17	-
Compressive Strength	EN 1926	(MPa)	116.11	Dry
Tensile Strength	ISRM 1981	(MPa)	8.4	Dry
Flexural Strength	EN 12372	(MPa)	26.8	Dry
Resistance to Salt Crystallization	EN 12370	(Mass loss %)	-0.11	After 48 Cycles
Resistance to Freeze-Thaw	EN 12371	(Mass loss %)	-0.04	After 48 Cycles
Resistance to Acid (H2SO4)	EN 13919	(Mass loss %)	-0.01	After 48 Cycles
Thermal Shock	EN 14066	(Mass loss %)	-0.01	After 48 Cycles

Details


Formats Available | Slabs

Thickness Available | 2cm, 3cm

Available Designs | Dune, Magma

Applications | Interior and Exterior Wall Cladding

Designs



Dune Design



Magma Design